



255 Fountain Street Akron, Ohio 44304-1991  
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

## VULCANIZED VEGETABLE OIL

### AKROFAX™ 758 WHITE SULFURLESS

#### PRODUCT DESCRIPTION:

Akrofax 758 Sulfurless is an oil-resistant (due to being made from castor oil) vulcanized vegetable oil. It was originally designed for millable urethanes but its usage has expanded to fluorocarbons, HNBR and other peroxide cured compounds where sulfur cannot be tolerated. Akrofax 758 is also used in PVC to improve extrusion and flow properties. Its white color is ideal for non-black compounds.

#### TYPICAL PROPERTIES:

N-hexane Extract . . . . .	32%
Free Sulfur. . . . .	0%
Mineral Oil . . . . .	29%
Ash . . . . .	< 1%
Specific Gravity . . . . .	0.98
Physical Form . . . . .	crumb

#### FUNCTIONS:

- Capacity for absorbing large amounts of mineral oils and other liquid plasticizer on mill and banbury.
- To speed the incorporation of fillers and to increase milling efficiency.
- To reduce migration of oils and plasticizers to the surface in low durometer stocks.
- To provide a non-thermoplastic firmness in uncured compounds which strengthens extruded sections and minimizes distortions in open steam cures. Gives soft compounds enough firmness to push out entrapped air.
- Ability to flow or promote flow under mechanical pressure.
- To provide a unique surface finish and supple feel to vulcanized rubber goods.
- To improve ozone resistance of the rubber compounds.
- To reduce compound nerve and improve smoothness of extrusions and calendared sheets.
- Plasticizer that results in minimum extraction

tc072111, t-fx758.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.