



255 Fountain Street Akron, Ohio 44304-1991
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

ZINC PRODUCTS
-SPECIALTY ZINC OXIDES-

ZINC OXIDE FP-CN

PRODUCT DESCRIPTION:

ZnO FP-CN (E-19577) is a specially treated zinc oxide made from high purity zinc designed to improve scorch time in carboxylated nitriles. It can replace zinc peroxide dispersions at a much lower cost (use part-for-part on an active material basis). Typical dosage is 5.0 phr in carboxylated formulas.

The ZnO FP-CN can also improve shelf life and scorch of ZnO-crosslinkable polymers like polychloroprene, chlorobutyl, or bromobutyl.

TYPICAL PROPERTIES:

Specific Gravity	5.57
Percent Active	100%
Appearance.....	off-white powder
Surface Area, m ² /g.....	3.2
Median Particle Size, microns.....	0.37
Package	50 pound net weight bags

CHEMICAL DISPERSIONS:

ZnO FP-CN is also available as Akroperse[®] ZnO/CN-80/NBR. This polymeric masterbatch contains 80% ZnO FP-CN and has a specific gravity of 2.89. Polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality and raw material control.

COMPARISON TO STRUKTOL ZP-1014 AND KADOX 911C:

Test Formulation:

<u>Chemical</u>	<u>phr</u>
Krynac X7.50	100.00
N550 Black	40.00
DIDP Plasticizer	6.00
Stearic acid	2.00
MC-98 Sulfur	1.25
<u>TMTM</u>	<u>1.50</u>
Total	150.75

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.

	<u>ZP-1014</u>	<u>Kadox 911C</u>	<u>ZnO FP-CN</u>
Test Formulation	150.75	150.75	150.75
Struktol ZP-1014	10.00	---	---
Kadox 911C	---	5.00	---
Akrochem ZnO FP-CN	---	---	5.00
ML Scorch @ 125°C			
Minimum	27.20	31.77	28.88
T ₂	7.50	3.90	7.13
T ₁₀	18.03	6.20	12.97
Rheometer - Micro die, 165°C, 3° arc			
Minimum, lb-in	9.0	9.0	9.0
T ₂ , minutes	2.6	1.6	2.8
T ₉₀ , minutes	7.2	5.6	6.8
Max Torque, lb-in	80.0	99.5	92.0
T ₉₀ - T ₂ , minutes	4.6	4.0	4.0

Typical Physical Properties: (cured to T₉₀ @ 165°C)

Hardness, Shore A	79	84	80
Tensile Strength, MPa	24.6	27.6	24.6
Elongation, %	475	395	425
Modulus, 100%, MPa	3.6	5.4	4.3
Modulus, 300%, MPa	13.6	19.7	15.2
Tear, die C, kN/m	39.2	40.8	42.8
DIN Abrasion Loss, (mm ³)	95.0	94.0	95.0
Specific Gravity	1.14	1.13	1.13