



255 Fountain Street Akron, Ohio 44304-1991
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RUBBER CHEMICALS
-ANTIOXIDANTS-
NON-STAINING

ANTIOXIDANT 60
(2-Mercapto-4(5)-Methylbenzimidazole)

PRODUCT DESCRIPTION:

Antioxidant 60 (2-mercapto-4(5)-methylbenzimidazole) is a non-discoloring and non-staining antioxidant for natural and synthetic rubbers, except polychloroprene. Protection against heat and oxygen aging is excellent, especially when combined with amine or phenol type antioxidant, wherein a synergistic effect yields results superior to those of the separate constituents. Also acts as a metal deactivator when used synergistically with Antiozonant PD-1 (black compounds) or Antioxidant 1024 (non-black compounds).

TYPICAL PROPERTIES:

Appearance.	yellow-white micro-granule (oil-treated)
Specific Gravity	1.25
Melting Point	290°C (554°F) minimum
Oil Content	1.5%
Storage Stability.	over two years

APPLICATIONS:

In addition to its antioxidant properties, Antioxidant 60 provides improved protection against rubber poisons, especially in combination with Antioxidant 33 or 235, or Antiozonants PD-1 or PD-2. It also imparts steam resistance to rubber compounds and has a brightening effect on transparent goods.

In spite of its high melting point, Antioxidant 60 disperses readily in rubber mixes. It does have a slight retarding effect in sulfur cures and reduces modulus slightly. Maximum protection is provided in thiuram and dithiocarbamate curing systems containing little or no sulfur.

For general applications, 0.6 - 1.5 phr Antioxidant 60 is used. For heat resistant thiuram cured compounds, 2 - 3 phr is used, or 1 - 2 phr in combination with 1 - 2 phr Antioxidant DQ, Antiozonant PD-1 or PD-2.

sb0903
 t-AO 60.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.