



255 Fountain Street Akron, Ohio 44304-1991  
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

## ELASTOMERS -NATURAL RUBBER-

### CLARIMER CV(60), L & L (Strippable)

#### PRODUCT DESCRIPTION:

CLARIMER natural rubber grades are high quality. They are extremely clean, very light colored and low odor. They are produced from field latex under closely controlled conditions. The CV (60) grade is viscosity controlled.

#### TYPICAL PROPERTIES:

<i>Natural Rubber: Grades</i>	<i>CV (60)</i>	<i>L</i>	<i>L (strippable)</i>
<b>Color Limit-Lovibond Scale, (max)</b>	4.5	3.5	3.5
<b>Dirt Content (less than), %</b>	0.02	0.02	0.02
<b>Ash Content (less than), %</b>	0.5	0.5	0.5
<b>Nitrogen Content (less than), %</b>	0.6	0.6	0.6
<b>Volatile Matter (less than), %</b>	0.8	0.8	0.8
<b>Plasticity Retention Index (min), %</b>	65.0	60.0	60.0
<b>Mooney Viscosity (ML 1+4 @ 100°C)</b>	55 - 65	- - -	58 - 68
<b>Acetone Extract, %</b>	3.5	3.5	3.5

#### PACKAGING:

Heavy strippable polyethylene film: A 2 mil white polyethylene wrap can be obtained by special order and is usually designated "strippable". In fact, it must be stripped and discarded as it will not properly mix into the polymer, even in an internal mixer.

The regular transparent polyethylene wrap is a very thin, low melt type that is not usually separated from the rubber before mixing.

gpb- 1/11, t-CLARIMER natural rubbers.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.