



255 Fountain Street Akron, Ohio 44304-1991
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RESINS & TACKIFIERS -PHENOLIC-

P-133 RESIN -THERMOPLASTIC-PHENOLIC RESIN-TACKIFIER-

PRODUCT DESCRIPTION:

P-133 is a thermoplastic, alkyl phenolic resin in a free-flowing flake form.

TYPICAL PROPERTIES:

Specific Gravity.....	1.04
Acid Number.....	35
Melt Point (ball & ring).....	97°C
Viscosity (Gardner-Woldt).....	0
(toluene - 64% Resin)	

STORAGE:

P-133 is a stable material with no tendency to change in physical properties when stored under normal conditions.

SOLUBILITY:

Soluble in esters, ketones, aromatic and aliphatic chlorinated hydrocarbons. Insoluble in alcohols.

COMPATIBILITY:

Excellent compatibility in synthetic and natural rubbers. Easily blended into rubber stocks.

RECOMMENDATIONS:

P-133 develops high tack levels in rubber compounds which are used in tire construction and mechanical goods. This resin provides tack in elastomers that are usually difficult to tackify, such as EPDM. Excellent tack can be obtained at lower levels of concentration than is possible with conventional tackifiers, such as P-90.

SHIPPING CONTAINERS:

Standard container is a 50 pound bag.

PRECAUTIONARY LABELLING:

CAUTION: MAY CAUSE IRRITATION. Avoid prolonged contact with skin. Avoid prolonged breathing of vapor or dust. Use with adequate ventilation.

cz121592, T-P133.DOC