



255 Fountain Street Akron, Ohio 44304-1991
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RESINS & TACKIFIERS
-PHENOLIC-

P-172 RESIN

PRODUCT DESCRIPTION:

P-172 is a heat reactive, phenolic resin used in the resin curing of various elastomer systems. It is supplied as a solution in rubber processing oil.

TYPICAL PROPERTIES:

Form.....	Liquid
Appearance.....	Clear to yellow
Solvent	Refined, Heavy Paraffinic Distillate
Specific Gravity	0.925
Viscosity @ 50°C, Poise	1.5 – 4.0
Methylol Content, %.....	2.6 – 4.2

SOLUBILITY:

P-172 has excellent compatibility in most elastomer systems.

STORAGE:

P-172 should be stored under conditions that do not exceed 86°F (30°C). Product has a one year shelf-life from the date of manufacture. As with all phenolic resins, P-172 will darken with age.

SHIPPING CONTAINER:

Supplied in bulk truckloads only.

wol – 4/26/10, T-P-172

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.