



255 Fountain Street Akron, Ohio 44304-1991  
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

**RESINS & TACKIFIERS**  
**-ADDITIONAL RESINS-**

**AKROCHEM<sup>®</sup> C595 RESIN**

**PRODUCT DESCRIPTION:**

C595 Resin is a light colored C<sub>5</sub> type resin which provides superior tackifying action to synthetic and natural rubber applications.

**TYPICAL PROPERTIES:**

Soften Point °C .....	90-100
Color, Gardner .....	7.0 max
Acidity % (mgKOH/g).....	.0.50 max
Ash %.....	.0.10 max
Packaging.....	.55.1 pound net weight drums

**APPLICATIONS:**

C595 Resin aids in processing elastomers and plastic products by increasing green tack, rate of incorporation of fillers and pigments, and provides wetting action for fillers. In addition, C595 Resin improves rubber to metal/fibers bonding. Common applications include hot melt adhesives, general tackifier and/or softener in NR and synthetic elastomers.

Gb60210, Akrochem C595 Resin

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.