



255 Fountain Street Akron, Ohio 44304-1991
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RUBBER CHEMICALS
-RETARDERS-

RETROCURE® G

COMPOSITION:

Blend of 4- and 5- methylbenzotriazole (tolyltriazole).

TYPICAL PROPERTIES:

Form.....	Light beige granules
Active substance content.....	98.0% minimum
Specific gravity @ 73 F/23 C	Approx. 1.24 gram/cm ³
Melting point.....	Approx. 181 F/83 C

APPLICATION:

Retrocure G is a pre-vulcanization retarder for sulfur modified (G type) polychloroprene rubbers (CR) but not for mercaptan modified grades (W type). It is also extremely effective in halobutyl rubbers (CIIR, BIIR).

Retrocure G is easily incorporated into rubber compounds. It effectively improves the scorch safety and bin storage stability of sulfur modified polychloroprene stocks without or with additional accelerators, such as ETU. Also, the scorch of nitrile rubber compounds with MBTS/sulfur vulcanization systems is improved significantly. Halobutyls are retarded with minimal loss of cure state or time to full cure.

Typical levels of addition based on 100 parts by weight of elastomer are 0.5 - 1.0 phr for polychloroprene and 0.2 - 0.5 phr for nitrile rubber.

Rubber goods containing Retrocure G have not been found to discolor or stain when used as recommended. Also, the mechanical properties of rubber compounds are practically not affected, including flexcracking and heat build-up properties. Due to the fairly high melt point, Retrocure G should not be added on a mill.

PACKAGING:

Retrocure G is packaged in 220 pound fiber drums.

t-retrocureg, tc 1111

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.