



255 Fountain Street Akron, Ohio 44304-1991  
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

**RUBBER CHEMICALS**  
**-ACCELERATORS-**  
**THIOUREAS**

**AKROFORM<sup>®</sup> ETU-22 PM**

**-75% Ethylene Thiourea-**

**PRODUCT DESCRIPTION:**

Accelerator ETU-22 PM imparts a high state of cure to neoprene compounds. It can be used alone or with other accelerators to obtain the desired processing safety and vulcanizate properties. Its use eliminates any dusting or handling of the powder.

**TYPICAL PROPERTIES:**

Appearance.....	Off-white pellet
Odor .....	Slight/Typical
Specific Gravity .....	1.20 calc.
Melting Point.....	200°C for active ETU-22
Dispersion .....	Easily disperses in dry polymers
Discoloration.....	Non-staining and non-discoloring
Binder System.....	Ethylene Propylene Rubber

**HANDLING PRECAUTIONS:**

When using this product, care should be taken to avoid skin contacts and where such has occurred, wash with soap and water. These precautions are indicated by a considerable quantity of toxicological data that has been published regarding the active ETU-22 Accelerator that composes 75% of this product.

**CHEMICAL DISPERSIONS:**

Polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality & raw material control.

Akrochem polymer bound or encapsulated dispersions eliminate any irritating dust, as well as other potential hazards in handling powders in the plant. The physical form is easy to handle and weigh accurately. As a dispersion masterbatch better uniformity of the mix at low process temperatures are possible.

gpb 2/19/10  
t-etu-22pm

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.