




255 Fountain Street Akron, Ohio 44304-1991
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947



WAXES
-PETROLEUM-

AKROWAX™ 5026

PRODUCT DESCRIPTION:

AKROWAX 5026 is a proprietary blend of microcrystalline wax and a high melt-point paraffin wax. It is designed for maximum protection of rubber articles exposed to high ozone levels at elevated temperatures (as in an ozone test chamber). Typical loadings are 2 to 4 phr in a normal application; 4 to 8 phr in highly loaded compounds.

This wax complies with F.D.A. Regulations for use as indirect or direct food additives described in Code of Federal Regulations, Title 21, Chapter 1, Section 172.886 and 178.3710 as well as 177.2600, Rubber Articles Intended For Repeated Use.

TYPICAL PROPERTIES:

Appearance.....	Beads
Melt Point (ASTM D-87).....	154°F
Color, Saybolt	+ 25
Specific Gravity	0.91
Needle Penetration, 77°F	10-14

wol - 7/10, t-akrowax 5026.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.