



3770 EMBASSY PARKWAY AKRON, OHIO 44333
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

CHEMICALS
-COUPLING AGENT-

RUCOGRIP B-VTM
Vinyl[tris(2-methoxyethoxy) silane]

PRODUCT DESCRIPTION:

Rucogrip B-VTM is a vinyl-functional alkoxy silane. It is a versatile silane that is often used as a coupling agent in mineral-filled EPM and EPDM cables and is also used in silane-modified polymers. It also has shown benefits as an adhesion promoter in paints and coatings and is easily incorporated into water-based systems.

TYPICAL PROPERTIES:

Appearance	Clear to slight yellow liquid
Purity (GC), %	97.00 – 100.00
Specific Gravity (25°C).	1.020 – 1.050
Boiling Point, 2 mm Hg.	285°C (545°F)
Flash Point.	92°C (198°F)
Refractive Index nD (25°C).	1.4170 – 1.4310
Standard Packaging.	200 KGS (441 LBS)

tee1/29/2026
t-rucogrip b-vtm st # 61454

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.