



3770 EMBASSY PARKWAY, AKRON, OHIO 44333
330-535-2100 ♦ 800-321-2260 ♦ FAX 330-535-8947

ELASTOMERS -NATURAL RUBBER-

SIR 10 & SIR 20

PRODUCT DESCRIPTION:

SIR (Standard Indonesian Rubber) are natural rubbers graded by technical specifications, not by the conventional visual standards. These SIR Rubber are produced from field grade coagulum (cuplump) from the Hevea brasiliensis tree grown in Indonesia.

TYPICAL PROPERTIES & SPECIFICATIONS:

<u>Grades:</u>	<u>SIR 10</u>	<u>SIR 20</u>	<u>Test Method</u>
Dirt Content, % wt. (Max)	0.10	0.20	ISO 249
Ash Content, % wt. (Max)	0.10	1.00	ISO 247
Nitrogen Content, % wt. (Max)	0.60	0.60	ISO 1656
Volatile matter, % wt. (Max)	0.80	0.80	ISO 248
Plasticity Retention Index, (Min)	60.0	50.0	ISO 2930
Wallace Rapid Plasticity Po, (Min)	30.0	30.0	ISO 2007

PACKAGE AND FORM:

SIR polymers are shrink-wrapped on a wood or plastic base pallet.

Per bale, 35 kg +/- 0.5 kg (or 77.1 lb)

Per pallet, net, 1260 kg (or 2,778 lb)

STORAGE:

Store in original packaging away from direct sunlight and sources of heat.

tee 11/6/19, SIR 10 & SIR 20 Natural Rubber

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.