



255 Fountain Street Akron, Ohio 44304-1991
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

FIRE RETARDANTS

HYMOD™ M932 SP

-vinyl silane treated alumina trihydrate-

PRODUCT DESCRIPTION:

Hymod M932SP and is a high performance, high surface area, low particle size alumina trihydrate (ATH or hydrated alumina) utilized as flame retardants and smoke suppressants in elastomeric applications. ATH is the most frequently used flame retardant in the world. The Hymod M932SP grade is a vinyl silane treated ATH for improved processing and physical properties of thermoset and thermoplastic compounds. ATH is a very effective flame retardant due to its thermodynamic properties which absorb heat and release water vapor. Alumina trihydrate releases its 35% water of crystallization as water vapor when heated above 205°C. The resulting endothermic reaction cools the product below flash point, reducing the risk of fire and acts as a vapor barrier to prevent oxygen from reaching the flame. Typical loadings vary from 20 phr to 150 phr. Because many polymers like polyethylene and polypropylene process above 200°C, these polyolefins should use magnesium hydroxide as a flame retardant filler since its water of hydration releases at approximately 325°C.

TYPICAL PROPERTIES:

Chemical Decomposition.....	Al (OH) ₃ → Al ₂ O ₃ - 3H ₂ O
Al (OH) ₃	99.2%
Loss on Ignition	34.6%
SiO ₂	0.005%
Fe ₂ O ₃	0.007%
Na ₂ O.....	0.30%
Median Particle Size μ.....	2.0
Surface Area m ² /g.....	12.0
Oil Absorption.....	38
Free Moisture % (105°C).....	0.8

Many other grades are available incorporating an assortment of chemical treatments including mercapto, epoxy, and other silanes, stearates and wetting agents. These grades may be made-to-order items with limited inventory. Please check with your sales representative for current product status and minimum purchase requirements.

Hymod is a trademark of J.M. Huber, Engineered Materials Sector

gpb 9/10, Hymod M932SP

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.