



3770 EMBASSY PARKWAY AKRON, OHIO 44333
 330-535-2100 ♦ 800-321-2260 ♦ FAX 330-535-8947

RUBBER CHEMICALS
-ANTIOXIDANTS-
NON-STAINING

ANTIOXIDANT 235

[2,2'-Methylene-bis-(4-methyl-6-tert-butyl-phenol)]

DESCRIPTION:

Antioxidant 235 fills the need for an effective antioxidant that is resistant to migration and surface loss. It has low volatility, gives very good protection against oxidation, non-staining and low in toxicity.

TYPICAL PROPERTIES:

Appearance.	Off-white crystalline powder
Melting Point.	128°C (minimum)
Ash.	0.25% maximum
Specific Gravity.	1.04
Solubility.	Slightly soluble in n-hexane, soluble in: ethanol, acetone, ethylene chloride and benzene, insoluble in water.

GENERAL RECOMMENDATIONS:

In Elastomers, Antioxidant 235 is outstanding in protecting white or light-colored rubber stocks, such as medical equipment, rubber thread, and latex compounds. It is effective in natural rubber, polybutadiene, butadiene-styrene copolymers, polyisoprene, chloroprene, and many other elastomeric materials. Normal treating levels range from 0.25 to 1.5 parts on the rubber hydrocarbon. At these levels, this antioxidant does not create a "bloom" on the stock and has no deleterious effect on the rate of cure or on physical properties. Antioxidant 235 will "pink" in white compounds upon exposure to sunlight.

In plastics, the physical properties of Antioxidant 235 make it an outstanding oxidation inhibitor for many high polymer plastic materials. It should be added in concentrations from 0.25% to 0.50% by weight of the polymer, the lower figure being adequate for most applications.

tee 3/21/2023
 t- ao 235 (st # 04160)

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.