



3770 Embassy Parkway Akron, Ohio 44333
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

ELASTOMERS
-NITRILE/PVC-

RUBALOY 2530
NBR/PVC/OIL

PRODUCT DESCRIPTION:

RUBALOY 2530 is unique blend of 50% acrylonitrile (NBR) and 50% polyvinyl chloride (PVC) with 75% DINP oil. Rubaloy 2530 can be easily processed on conventional rubber mixing/compound machines, has excellent filler and plasticizer absorption properties, and can withstand elevated compounding temperatures. It provides substantial tensile strength considering the level of plasticizer. Rubaloy 2530 can be sulfur and peroxide cured. A slightly higher level of accelerators is recommended.

TYPICAL PROPERTIES:

Appearance	Yellow Cream Sheets
Specific Gravity	1.07± 0.02
Mooney Viscosity, ML (1+4) @100°C	50±5
Nitrile/ PVC/DINP Oil Content, %	50/50/75
ACN, Content	Medium
Hardness Raw Polymer.....	50±5

APPLICATION:

RUBALOY 2530 can be used in a variety of rubber compounding applications such as: low hardness printing rolls, molded articles, low density foam, soft pipes, tubes, and hoses.

PACKAGE AND FORM:

RUBALOY 2530 comes in 55 lb. bags

STORAGE:

Store in original packaging away from direct sunlight and sources of heat.

rh 2/17
 x-RUBALOY 2530

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.