



3770 Embassy Parkway, Akron, Ohio 44333
330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947



ELASTOMERS
-NITRILE/PVC-

RUBALLOY - VL 7360P
NBR/PVC

PRODUCT DESCRIPTION:

RUBALLOY VL7360P is a non-staining, oil, ozone, abrasion, weather and flex resistant polymer blend. The NBR portion of the blend utilizes a very low ACN content polymer (22%). RUBALLOY – VL 7360P can be compounded to provide low temperature service easily to withstand -55°C. It is a poly-blend of 70% NBR and 30% PVC. This grade offers exceptional rubber-to-metal bonding as well.

TYPICAL PROPERTIES:

Appearance	Yellow Cream Sheets
Specific Gravity	1.04± 0.02
Mooney Viscosity, ML (1+4) @100°C	62±5
Nitrile / PVC Content, %	70/30
ACN, Content	Low (22%)
Hardness Raw Polymer.....	60±5

APPLICATION:

RUBALLOY – VL 7360P can be used in a variety of rubber compounding applications such as: molded gaskets, oil-fuel seals, o-rings, extrusions, grommets, industrial and hydraulic hoses, high hardness compounds, sponge, and automotive applications. It is also used to pass ASTM ozone and fuel requirements.

PACKAGE AND FORM:

RUBALLOY L7360P standard unit is packaged as a 55.1 lb. bag (25 KG).

STORAGE:

Store in original packaging away from direct sunlight and sources of heat.

X-RUBALLOY – VL 7360P (ST#-66972)
TLM 3-25-2019

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.