



255 FOUNTAIN STREET AKRON, OHIO 44304-1991
 330-535-2100 ♦ 800-321-2260 ♦ FAX 330-535-8947

MAGNESIA PRODUCTS
-ADDITIONAL DISPERSIONS-

AKRO-MAG® BARS
-GREEN LABEL MgO-

PRODUCT DESCRIPTION:

AKRO-MAG BARS are a new form of magnesium oxide. The bar is a dispersion of naphthenic process oil, with the magnesium oxide powder having a typical Iodine absorption figure of 115 on the Morton Activity Index. The properties of activity and particle size of the magnesia are the most important characteristics in determining the final properties of the vulcanized polychloroprene, Hypalon and fluoroelastomers.

The two Akrochem® MgO Bar Grades (Blue and Green) offer a choice of MgO activity and price. Blue offers the most active grade and thus the most scorch resistance in halogenated polymers like polychloroprene. Green bar offers a less active grade MgO that results in faster scorch and cures times.

PHYSICAL CHARACTERISTICS:

Magnesium Oxide, MgO, Green Bar.....	58%
Carrier	Naphthenic Oil
Consistency.....	Stiff Paste
Color	Cream to Dark Tan
Specific Gravity, Calculated.....	1.58
Average MgO Surface Area (m2/gm)	115
Bar Weight.....	3.0 lbs.
Bar Size.....	Approx. 2" x 3" x 9"
Wrapping	16-3 lb. Bars/Box 48 lbs./Box
Box Size.....	13" X 10" X 8 1/4" High

STORAGE STABILITY:

AKRO-MAG Bars have excellent storage stability and will show little change in consistency, shape, color or ease of dispersion with prolonged aging.

USAGE:

The recommended level is at 4 PHR or as a direct replacement to the dry magnesium content used in the polychloroprene formulation. The combined effects of the pre-wetted and dispersed magnesia give a synergistic effect to the dry Magnesium Oxide in most formulations.

wol - 3/10, T-greenbar.doc

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.