



3770 EMBASSY PARKWAY AKRON, OHIO 44333
 330-535-2100 ♦ 800-321-2260 ♦ FAX 330-535-8947

RUBBER CHEMICALS
-ACCELERATORS-
SULFENAMIDES

Akrochem Accel CBTS Powder
(N-cyclohexyl-2-benzothiazole sulfenamide)

PRODUCT DESCRIPTION:

Akrochem Accel CBTS is a delayed action sulfenamide accelerator for use in natural and synthetic rubbers. It can be compounded alone or in combination with many secondary accelerators. CBTS (sometimes referred to as CBS) provides slightly more scorch safety than BBTS.

TYPICAL PROPERTIES:

Appearance	off-white powder
Melting Point	98°C (min.)
Ash.....	0.30% (max.)
Assay.....	95.0% (min.)
Heat Loss	0.30% (min.)
Specific Gravity	1.27
Packaging.....	44.1 pound bag

APPLICATION:

CBTS yields better scorch resistance than thiazoles. It can be accelerated by thiurams and dithiocarbamates to give shorter cure times. CBTS is non-blooming, but slightly dis-coloring. The recommended dosage range is 0.5 - 3.0 PHR, with the higher level typically being used in concert with an efficient vulcanization (EV) systems and reduced sulfur levels.

CHEMICAL DISPERSIONS:

Akrochem Accel CBTS is also available as a polymeric masterbatch (CBS-75/EPR). Polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality and raw material control.

rh 6/28/21
 T-cbts powder (# 1408)

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.