



3770 Embassy Parkway Akron, Ohio 44333
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

**RUBBER CHEMICALS
 -ACCELERATORS-
 THIURAMS**

ACCELERATOR DPTT

(Dipentamethylene Thiuram (Tetra/Hexa Sulfide*) Polysulfide Mixture)

PRODUCT DESCRIPTION:

Accelerator DPTT is a non-discoloring and non-staining accelerator. It is a very active sulfur-bearing accelerator and contains approximately 25% available sulfur. DPTT imparts unusually good heat resistance to sulfurless compounds and may be used as a primary accelerator for Hypalon and Butyl as well as an excellent secondary accelerator for EPDM. It can also be used as a vulcanizing agent for heat resistant latex.

TYPICAL PROPERTIES:

Appearance	light gray to buff powder
Melting Point	113°C
Heat Loss.	0.5%
Ash Content	0.5%
Specific Gravity	1.50
Packaging.	55.1 pound bag

* Some producers have named their similar product “tetrasulfide”; others call it “hexasulfide”. It is both, as all products of this type are a blend of the two forms.

HANDLING PRECAUTIONS:

Akrochem DPTT may cause skin irritation in some individuals. Avoid prolonged or repeated contact with skin. Avoid breathing dust or vapor. Use with adequate ventilation.

CHEMICAL DISPERSIONS:

Accelerator DPTT is also available as Akroform® DPTT-70/EPR/P (pellets). This polymeric masterbatch contains 70% Accelerator DPTT and has a specific gravity of 1.29.

Akrochem polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality & raw material control. They eliminate any irritating dust, as well as other potential hazards in handling powders in the plant. The physical form is easy to handle and weigh accurately. As a dispersion, better uniformity of the mix at low process temperatures are possible.

tee 7/30/2020
 x-dptt

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.