



3770 Embassy Parkway, Akron, Ohio 44333

330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RUBBER CHEMICALS
-ACCELERATORS-
DITHIOCARBAMATES

ACCELERATOR MZX*

(Zinc Dimethyldithiocarbamate)

PRODUCT DESCRIPTION:

Accelerator MZX* is a very active non-discoloring, non-staining accelerator for NR, IR, BR, SBR, IIR and EPDM rubbers, as well as NR latex. It is generally used as a secondary accelerator with the thiazoles. It is very effective in EPDM because of its activity. However, it may cause blooming in EPDM compound when used above 0.8 part per hundred of rubber.

TYPICAL PROPERTIES:

Specific Gravity	1.71
Purity - min %	MZX - 98
Appearance	off-white powder
Melt Point, °F (°C)	464 (240) min.
Solubility.....	insoluble in water and aliphatic hydrocarbons, moderately soluble in aromatic hydrocarbons.

* Accelerator MZX is an oil treated version. Akrochem only offers the treated version due to inhalation hazards associated with untreated powder.

CHEMICAL DISPERSIONS:

Accelerator MZX* is also available as Akroform® ZDMC-75/EPR/P. This polymeric masterbatch contains 75% Accelerator MZ and has a specific gravity of 1.38. Polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality and raw material control.

T-MZX & ZDMC-75
TLM 1/9/2018

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.