



3770 Embassy Parkway Akron, Ohio 44333

330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

RUBBER CHEMICALS  
-ANTIOXIDANTS-  
NON-STAINING

**ANTIOXIDANT 1076**  
**Stearyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate**

**DESCRIPTION:**

Antioxidant 1076 is a non-staining, high molecular weight, hindered phenolic antioxidant. Because of its low volatility, Antioxidant 1076 imparts excellent heat stability and color retention, with good compatibility and low extractability.

**TYPICAL PROPERTIES:**

Appearance	white powder
Melt Point	49°C - 54°C
Ash Content	0.1% max.
Volatile Matter	0.2% max.
Solubility at 20°C	Acetone(26%), Benzene(57%) Chloroform(57%), Ethyl Acetate(42%) Hexane (31%), Methyl Alcohol (0.6%) Water (0.01%)

**APPLICATION:**

Antioxidant 1076 finds application in plastics, rubber, latex, varnishes, adhesives, TPR's and Hot Melts. In plastics, antioxidant 1076 provides excellent antioxidant performance in Polyethylene, Polystyrene, Polyacetal, PVC, AS resin, Methacrylic resin, Polycarbonate, Polyester, and Polymethyl-pentene as well as many others. In rubbers, Antioxidant 1076 can be used in SBR, EPR, EPDM, Polybutadiene, Neoprene, Nitrile, Polyisoprene, and many other synthetic rubbers. Typical dosage is 0.02% - 0.5% by weight.

**PACKAGING:**

110 pound carton

rh 4/19  
X-ao 1076

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.