



3770 EMBASSY PARKWAY AKRON, OHIO 44333
 330-535-2100 ♦ 800-321-2260 ♦ FAX 330-535-8947



CHEMICAL DISPERSIONS
-MASTERBATCHES-

Perkadox® BC-EP40
Dicumyl Peroxide

PRODUCT DESCRIPTION:

Perkadox BC-EP40 is an organic dialkyl peroxide chemically identified as dicumyl peroxide dispersed in a polymeric binder. Dicumyl peroxide is used as a cross-linking agent for synthetic and natural elastomers and polyolefins such as polyethylene and ethylene vinyl acetate. This peroxide is noted for its non-blooming characteristic and high reactivity at medium processing (maximum safe processing temperature is about 130°C) and curing temperatures (optimum curing temperature is 165°C +/- 10°C).

TYPICAL PROPERTIES:

Appearance:	off-white granules
Peroxide Content (%)	40
Specific Gravity	1.20
Packaging.....	55.1

APPLICATIONS:

Perkadox BC-EP40 is used as a catalyst for cross-linking any synthetic or natural elastomer or polyolefin that can be cured with peroxides. Due to its half life, this peroxide encompasses a good compromise of scorch safety and cure rate. Dicumyl peroxide has an approximate 10 hr., 1 hr. and 0.1 hr. half-life of 120 °C, 140°C and 185°C, respectively.

ADVANTAGES:

Polymer bound or encapsulated dispersions are a proven means of upgrading plant safety, efficiency, quality & raw material control.

Akrochem polymer bound or encapsulated chemical dispersions eliminate any irritating dust, as well as other potential hazards in handling powders in the plant. The physical form is easy to handle and weighs accurately. With a dispersion, better uniformity of the mix at lower processing temperatures is possible.

tee 5/25/2023, t-perkadox bc-ep40

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the

customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.