



255 Fountain Street Akron, Ohio 44304-1991  
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

## VULCANIZED VEGETABLE OILS

### AKROFAX™ 900C

#### TYPICAL PROPERTIES:

Acetone Extract .....	43%
Free Sulfur .....	0.3%
Mineral Oil.....	29%
Ash.....	10%
Specific Gravity.....	1.15
Physical Form.....	milled crumb

#### FUNCTION:

- Capacity for absorbing large amounts of mineral oils and other liquid plasticizer on mill and banbury.
- To speed the incorporation of fillers and to increase milling efficiency.
- To reduce migration of oils and plasticizers to the surface in low durometer stocks.
- To provide a non-thermoplastic structure in uncured compounds which strengthens extruded sections and minimizes distortions in open steam cures.
- Ability to flow or promote flow under mechanical pressure.
- To provide a unique surface finish and supple feel to vulcanized rubber goods.
- To improve ozone resistance of the rubber compounds.

b071195  
T-FX900C.DOC