



255 Fountain Street Akron, Ohio 44304-1991  
 330-535-2100 ♦ 800-321-2260 ♦ Fax 330-535-8947

**WAXES**  
**-POLYETHYLENE-**

**AKROWAX™ PE-LM**

**DESCRIPTION:**

Akrowax PE-LM is a low molecular weight polyethylene used as a process aid in natural and synthetic rubbers. Its outstanding compatibility and excellent flow and release characteristics make Akrowax PE-LM useful in almost every rubber compound. The "LM" version provides a lower drop or softening point than Akrochem's standard PE wax.

**TYPICAL PROPERTIES:**

Melt Point .....	105°C
Specific Gravity .....	0.92
Appearance .....	fine, white grains

**APPLICATIONS:**

Akrowax PE-LM may be used to:

- improve flow for injection and transfer molding, provide release from hot metal surfaces (internal mixers, hot calendar rolls, extruder dies, and molds)
- improve filler dispersion when added early in mix
- at higher loadings (>5phr), provide a glossier finish to cured parts

Akrowax PE-LM is typically used at the 2-6 phr level in virtually all elastomers (1 phr is the usual recommendation for fluoroelastomers). It provides release with minimal interference with adhesion properties. Note: for any PE wax to be effective it must be above melt point. Thus, PE waxes provide no release from mills but outstanding release from internal mixers and molds.

Normally up to 5 phr may be added to a compound with little effect on vulcanized properties. High loadings (up to 20 phr) can be used in EPDMs to achieve high durometer non-black stocks that process well. Akrowax PE-LM should be melted when dispersed in a compound to prevent molding flaws (streaky blisters are evidence of lack of melt).

Akrowax PE-LM's lower softening point can provide release from equipment at lower processing temperatures. For example, the temperature at which a stock releases from a calendar or an internal mixer might be lowered 10°C (say from 120°C to 110°C), thus reducing stock heat history.

Jh 0605, t-pe-lm

Included with its product literature and upon the request of its customers, Akrochem provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although Akrochem believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. Akrochem will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of Akrochem products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the customer must read

and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by Akrochem as to any such product, method, or process. AKROCHEM CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY AKROCHEM.